

SPECIALTY OPTICAL FIBER

IXF-PMF-1550-125-P-020-PI

Polarization-Maintaining Fiber

Exail proposes a range of standard PM Fibers with 125 μm cladding diameter.

Customized coatings and wavelengths available upon request.





Benefits & Features

- Operating temperature long term up to 300 $^{\circ}\text{C}$
- Operating temperature short term up to 350 $^{\circ}\text{C}$
- High birefringence
- Excellent polarization maintaining properties
- Low attenuation
- Dual-layer UV acrylate and 900 μm

Applications

- High temperature sensing
- Oil and gas



TECHNICAL SPECIFICATIONS

Parameters

Cutoff wavelength (nm)	1430 ± 50
Attenuation @1550nm (dB/km)	< 2
Beat length @1550nm (mm)	< 3.7
Mode field diameter @1550nm (μm)	6.6 ± 0.5
Numerical aperture	0.20 ± 0.01
Core/Clad concentricity (μm)	< 1
Cladding diameter (μm)	125 ± 1
Coating diameter (μm)	160 ± 5
Proof test level (kpsi)	100

Design parameters

Operating wavelength (nm)	1550
Design	Panda
Core ellipticity (%)	< 15
Holding parameter (m ⁻¹)	< 1.10 ⁻⁵
Coating material	Polyimide
Operating temperature range (°C)	-40 to +85

Exail reserves the right to change, at any time and without notice, the specifications, design, function or form of its products described herein.

contact.photonics@exail.com | www.exail.com
Europe +33 1 30 08 94 50 | Americas +1 508 745 3487 | APAC +60 11 1623 1698

