## SPECIALTY OPTICAL FIBER

IXF-2CF-EY-O-17-130-L Series

# Double Clad Er/Yb Co-Doped Fibers

IXF-2CF-EY fibers are double clad Erbium-Ytterbium co-doped fibers. The core composition has been carefuly selected in order to get high efficiency and low 1 µm emission ratio, which are the recognized trade mark of Exail Erbium-Ytterbium co-doped fibers developed over the past 10 years.

The octagonal shape of the 2nd cladding provides homogeneous pump signal transverse distribution over the multimode guide.

Refering to its low core NA, this fiber is singlemode and make it suitable for highest beam quality requirements

Dual coating with low index primary layer

For easy integration, matching passive fibers are available as well as pump combiners

### **Benefits & Features**

- Extensive Exail know-how in Er/Yb fibers core composition
- High efficiency & Power Conversion Efficiency
- Low 1 µm emission
- Easy to splice and cleave
- Large Mode Area fibers

#### **Applications**

- Lidar
- Mid Power Amplifier
- High Power Telecom & CATV Amplifier (L2)

### **Related Products**


- IXF-2CF-PAS-17-130-0.19
- IXF-PAS-17-130-0.19
- IXS-COMB-2-1-1-17-130-A

Version	L1	L2
Core diameter (µm)	17 ± 1	
Cladding diameter (flat/flat) (µm)	125 ± 3	
Cladding shape	Octagonal	
Coating diameter (µm)	245 ± 15	
Core NA	0.19 ± 0.02	
Cladding NA	≥ 0.46	
Clad absorption @915nm (dB/m)	4.5 ± 0.5	5.5 ± 0.5
Clad absorption @976nm* (dB/m)	18 ± 2	22 ± 2
Core absorption @1536nm (dB/m)	40 - 50	45 - 60
Multimode background losses (dB/km)	< 50	
Core-clad offset (µm)	< 1.0	
Proof test level (kpsi)	100	

\* Calculated from 915 nm absorption value

#### Comments:

HeNe multimode tested OTDR tested



Version= 1 or 2 (see table above)

Exail reserves the right to change, at any time and without notice, the specifications, design, function or form of its products described herein.



exail