

IXF-2CF-EY-PM-6-130-LNF-L Series

Double Clad Polarization-Maintaining Er/Yb Co-Doped Fibers

IXF-2CF-EY fibers are double clad Erbium-Ytterbium co-doped fibers. The core composition has been carefully selected in order to get high efficiency and low 1 μm emission ratio, which are the recognized trade mark of Exail Erbium-Ytterbium co-doped fibers developed over the past 10 years.



PM design of these fibers is Panda type which make it easy to be recognized by splicing machines.

Dual coating with low index primary layer

For easy integration, matching passive fibers are available.

Benefits & Features

- Panda fibers
- Extensive Exail know-how in Er/Yb fibers core composition
- High efficiency & Power Conversion Efficiency
- Low 1 μm emission
- Easy to splice and cleave
- Singlemode operation

Applications

- PM Amplifier
- High Power Telecom & CATV Amplifier

Related Products

- IXF-2CF-PAS-PM-6-130-0.21
- IXF-PAS-PM-6-130-0.21

Version	1	2
Core diameter (μm)	6 ± 0.5	
Cladding diameter (flat/flat) (μm)	125 ± 3	
Cladding shape	Round	
Coating diameter (μm)	245 ± 15	
Core NA	0.19 ± 0.02	
Cladding NA	≥ 0.46	
Clad absorption @915nm (dB/m)	0.6 - 0.9	0.8 - 1.2
Clad absorption @976nm* (dB/m)	2.4 - 3.6	3.2 - 4.8
Core absorption @1536nm (dB/m)	25 - 35	35 - 45
Multimode background losses (dB/km)	< 20	< 50
Birefringence	> 1.10 ⁻⁴	> 2.10 ⁻⁴
Core-clad offset (μm)	< 1.0	
Proof test level (kpsi)	100	

* Calculated from 915 nm absorption value

Comments:

HeNe multimode tested

OTDR tested

Power Conversion Efficiency (PCE) >35% (following XFS/080301ARL procedure)

Ordering information

IXF-2CF-EY-PM-6-130-LNF-L Version= 1 or 2 (see table above)

Exail reserves the right to change, at any time and without notice, the specifications, design, function or form of its products described herein.

contact.photonics@exail.com | www.exail.com
 Europe +33 1 30 08 94 50 | Americas +1 508 745 3487 | APAC +60 11 1623 1698